
Model No : NPG 100 -12 12 V 100 AH

DEEP CYCLE GEL BATTERY






Parameter Chart:


Volt	s						
Capacity((25°C)		100Ah				
Discharge Current Testing (25°C)			59Ah				
			79Ah				
Internal Resistance		Full	4mΩ				
			104%				
Capacity Affected By Temperature			100%				
			83%				
			-15°C				
Residual Capacity (25°C)		Capac	91%				
		Capac	82%				
9.62	, ,		Capacity After 12 Months Storage				
Charge (Constant Voltage)	Cycle (25°C)		Initial Charging Current Les Than 30A Voltage 14.5~14.9V				
voltage)	Float (25°C)	Charge Voltage 13.6~	13.8V			

[★]The above are average and data obtained from the firsr 3 charge/discharge cycles. These are not minimum values.

Residual Capacity




Discharge Current 25℃




Model No : NPG 100 -12 12 V 100 AH

DEEP CYCLE GEL BATTERY

Constant voltage charging characteristics



Cycle service life in relation to the depth of discharge



Constant Current Discharge Characteristics (A, 25°C)

F.V/Time	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60V	220.4	175.4	108.2	65.1	36.6	26.5	18.5	12.2	10.2	5.3
10.2V	209.4	168.3	104.2	62.5	36.1	26.1	18.2	12.1	10.1	5.3
10.5V	203.4	164.3	101.2	61.2	35.8	25.9	18.0	12.1	10.0	5.2
10.8V	196.4	160.3	99.00	59.4	35.4	25.6	17.8	12.0	10.0	5.2

Constant Power Discharge Characteristics (Watt, 25°C)

F.V/Time	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60V	2380.8	1925.8	1214.4	742.5	423.8	310.6	219.4	146.3	123.2	64.3
10.2V	2261.5	1848.7	1169.3	712.4	417.8	306.6	215.4	145.3	122.2	64.3
10.5V	2196.4	1803.6	1159.3	708.4	413.8	303.6	212.4	145.3	121.2	64.1
10.8V	2121.2	1760.5	1111.2	677.4	409.8	300.6	210.4	144.3	119.2	63.7

Capacity Factors With Different Temperature

Battery	Туре	-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%

★The above are average and data obtained from the firsr 3 charge/discharge cycles. These are not minimum values.











